

ICS: 77.160

Geregistreeerde Belgische norm

NBN EN ISO 3954

1e uitg., augustus 2008

Normklasse: P 51

Poeders voor gebruik in poedermetallurgie - Monsterneming (ISO 3954:2007)

Poudres pour emploi en métallurgie des poudres - Echantillonnage (ISO 3954:2007)

Powders for powder metallurgical purposes - Sampling (ISO 3954:2007)

Toelating tot publicatie: 19 december 2007

Vervangt NBN EN 23954 (1993).

Deze Europese norm EN ISO 3954:2008 heeft de status van een Belgische norm.

Deze Europese norm bestaat in drie officiële versies (Duits, Engels, Frans).



Bureau voor Normalisatie Brabançonnelaan 29 B-1000 Brussel België
Tel: +32 2 738 01 12 - Fax: +32 2 733 42 64 - E-mail: info@nbn.be - NBN Online: www.nbn.be
Bank 000-3255621-10 IBAN BE41 0003 2556 2110 BIC BPOT BEB1 BTW: BE 0880.857.592

*norme belge
enregistrée*

NBN EN ISO 3954

1e éd., août 2008

Indice de classement: P 51

Poudres pour emploi en métallurgie des poudres - Echantillonnage (ISO 3954:2007)

Poeders voor gebruik in poedermetallurgie - Monsterneming (ISO 3954:2007)

Powders for powder metallurgical purposes - Sampling (ISO 3954:2007)

Autorisation de publication: 19 décembre 2007

Remplace NBN EN 23954 (1993).

La présente norme européenne EN ISO 3954:2008 a le statut d'une norme belge.

La présente norme européenne existe en trois versions officielles (allemand, anglais, français).

English Version

Powders for powder metallurgical purposes - Sampling (ISO 3954:2007)

Poudres pour emploi en métallurgie des poudres -
Échantillonnage (ISO 3954:2007)

Pulver für die Pulvermetallurgie - Probenahme (ISO
3954:2007)

This European Standard was approved by CEN on 27 August 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....3

Foreword

This document (EN ISO 3954:2007) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy" in collaboration with Technical Committee CEN/SS M11 "Powder metallurgy", the secretariat of which is held by CMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2008, and conflicting national standards shall be withdrawn at the latest by March 2008.

This document supersedes EN 23954:1993.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 3954:2007 has been approved by CEN as a EN ISO 3954:2007 without any modification.

NBN EN ISO 3954 (2008)

NBN EN ISO 3954 (2008)
**INTERNATIONAL
STANDARD**

**ISO
3954**

Second edition
2007-09-01

**Powders for powder metallurgical
purposes — Sampling**

Poudres pour emploi en métallurgie des poudres — Échantillonnage



Reference number
ISO 3954:2007(E)

© ISO 2007

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3954 was prepared by Technical Committee ISO/TC 119, *Power metallurgy*, Subcommittee SC 2, *Sampling and testing methods for powders (including powders for hardmetals)*.

This second edition cancels and replaces the first edition (ISO 3954:1977), which has been technically revised.

Powders for powder metallurgical purposes — Sampling

1 Scope

This International Standard specifies procedures for the sampling of powders for powder metallurgical purposes.

It also covers the splitting of the sample into the quantity required for testing.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply (see also Figure 1).

2.1

lot

quantity of powder processed or produced under conditions that are presumed uniform

2.2

increment

quantity of powder obtained by a sampling device at one time from a single lot

2.3

gross sample

quantity of powder, adequate for the tests to be performed, consisting of all the increments taken from a single lot

2.4

composite sample

blended entire gross sample or part thereof

NOTE 1 Alternatively, it may be obtained by splitting the lot.

NOTE 2 However it is obtained, it is essential that it be thoroughly blended.

2.5

test sample

quantity of powder taken from the composite sample for determining a single property or for preparing test pieces

NOTE It is normally taken by splitting the composite sample.

2.5.1

test portion

definite quantity of powder drawn from the test sample (or, if both are the same, from the composite sample) and on which the test is carried out

2.5.2

test piece

test specimen

object of specified form prepared from a test sample