

ISO 18071:2016
NBN ISO 18071:2021

 **NBN**



**Fine ceramics (advanced ceramics, advanced technical ceramics)
– Determination of antiviral activity of semiconducting
photocatalytic materials under indoor lighting environment –
Test method using bacteriophage Q-beta (ISO 18071:2016)**

Valid from 26-05-2021

ICS: 81.060.30

**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Determination of antiviral activity
of semiconducting photocatalytic
materials under indoor lighting
environment — Test method using
bacteriophage Q-beta**

*Céramiques techniques — Détermination de l'activité antivirale
des matériaux photocatalytiques semi-conducteurs dans un
environnement d'éclairage intérieur — Méthode d'essai utilisant un
bactériophage Q-béta*



ISO 18071:2016(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Principle	3
6 Materials	3
6.1 Strains and preparation for tests.....	3
6.1.1 Strains.....	3
6.1.2 Bacteria preparation.....	4
6.1.3 Bacteriophage preparation.....	4
6.2 Media.....	5
6.2.1 General.....	5
6.2.2 1/500 Nutrient broth (1/500 NB).....	5
6.2.3 Calcium solution.....	5
6.2.4 LB broth with calcium.....	5
6.2.5 Agar powder.....	5
6.2.6 LB agar.....	5
6.2.7 Bottom agar plate (LB agar plate with calcium).....	6
6.2.8 Top agar.....	6
6.2.9 Soybean-casein digest broth with lecithin and polysorbate 80 (SCDLP).....	6
6.2.10 Peptone saline solution.....	6
7 Apparatus and equipment	6
7.1 Test equipment.....	6
7.2 Cover film.....	7
7.3 Moisture preservation glass.....	7
7.4 Glass tube or glass rod.....	7
7.5 Paper filter.....	7
7.6 Light source.....	7
7.7 UV sharp cut-off filter.....	8
7.7.1 Condition A (under 400 nm cut-off condition).....	8
7.7.2 Condition B (under 380 nm cut-off condition).....	8
7.8 Illuminance meter.....	8
7.9 Centrifuge.....	8
7.10 Sterilized syringe filter unit.....	8
8 Test piece	8
9 Procedure	8
9.1 General.....	8
9.2 Procedure for preparation of bacteria suspension.....	9
9.3 Procedure of preparation of test bacteriophage solution.....	9
9.4 Procedure of test for indoor-light-active photocatalytic antiviral activity.....	10
9.5 Indoor lighting condition.....	10
9.6 Measurement of titre of bacteriophage.....	11
10 Calculation	12
10.1 General.....	12
10.2 Test requirement fulfilment validation.....	12
10.3 Indoor-light-active photocatalyst antiviral activity value calculation.....	13
10.4 Antiviral activity value calculation without indoor-light-active photocatalyst.....	13
11 Test report	14

ISO 18071:2016(E)

Bibliography **15**

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 206, *Fine ceramics*.

ISO 18071:2016(E)

Introduction

This International Standard applies to testing the antiviral activity of indoor-light-active photocatalytic ceramics and other materials produced by either coating or mixing of a light-active photocatalyst. The International Standard for testing the antibacterial activity of photocatalytic materials has been published as ISO 27447 and the International Standard for testing the antibacterial activity of indoor-light-active photocatalytic materials has been published as ISO 17094. The International Standard for determination of antiviral activity of semiconducting photocatalytic materials has also been published as ISO 18061.

The test method for cloths or textiles is not included in this International Standard because of lack of indoor-light-active photocatalytic cloths or textiles. When the indoor-light-active photocatalytic cloths or textiles with antiviral activity using indoor-light-active photocatalytic activity have been developed, a test method for indoor-light-active photocatalytic cloths or textiles will be proposed with the glass adhesion method in ISO 27447.

Fine ceramics (advanced ceramics, advanced technical ceramics) — Determination of antiviral activity of semiconducting photocatalytic materials under indoor lighting environment — Test method using bacteriophage Q-beta

WARNING — Only personnel trained in microbiological techniques should carry out tests.

1 Scope

This International Standard specifies the determination of the antiviral activity of materials that contain indoor-light-active photocatalytic materials or have indoor-light-active photocatalytic films on the surface by a test method that measures the infectivity titre of bacteriophage Q-beta after illumination with indoor light.

NOTE In the test method, the surrogate microbe is bacteriophage Q-beta, intended as a model for influenza viruses.

This International Standard is intended for use with different kinds of indoor-light-active photocatalytic materials used in construction materials, in flat sheet, board or plate shape that are the basic forms of materials for various applications. It does not include powder, granular or porous indoor-light-active photocatalytic materials.

This International Standard is applicable to indoor-light-active photocatalytic materials produced for an antiviral applications. Other types of performance of indoor-light-active photocatalytic materials, i.e. antibacterial activity, antifungal activity, decomposition of water contaminants, self-cleaning, antifogging and air purification, are not determined by this method.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 14605, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Light source for testing semiconducting photocatalytic materials used under indoor lighting environment*

ISO 27447, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for antibacterial activity of semiconducting photocatalytic materials*

ISO 80000-1, *Quantities and units — Part 1: General*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

photocatalyst

substance that carries out many functions based on oxidization and reduction reactions under photoirradiation, including decomposition and removal of air and water contaminants, deodorization, and antiviral, antibacterial, antifungal, self-cleaning and antifogging actions